

Specification which includes the previous amendments. All the pages have been numbered correctly. Original Page 8 was revised to state that FIG. 1 shows pressure source 34, and that FIG. 2 shows vacuum source "34a." This is to be consistent with amended FIG. 2 to show "34a". No new matter has been introduced into the Substitute Specification.

The amendments to the claims are as follows. Claim 1 has been amended to delete the "whereby" clauses and phrases which were objected to by the Patent Examiner. Claim 1 was also revised in order to delete the reference numerals "(22,26; 40a)." Claim 1 was also revised to conform to the suggestion of the Patent Examiner to move the description of the hole-structure-creating unit down to step 3.

Claim 3 was amended to delete the terminology " and especially 50%." This claim language was then added back by presenting new claim 25.

Claims 5 and 6 were objected to as being improper dependent claims. In response thereto, claim 5 has been rewritten as an independent claim, which overcomes this objection.

Claims 8 and 9 have been amended in order to delete the

reference numeral "(34)." Claims 11,12 and 13 have been amended in order to delete the reference numeral "(22)." Claim 17 has been amended in order to delete the reference numeral "(26)."

Claims 19 to 24 have been revised so as to recite "a procedure" rather than reciting "a fleece." However each of claims 19 to 24 depend from claim 1, or depend from claim 19 which depends from claim 1.

Regarding claim 2 it is disclosed in the originally filed Specification on page 5, second paragraph for example, that an additional stiffening is achievable for example by applying heat and/or pressure.

Thus claim 2 was amended to recite that an additional stiffening step is performed. Regarding claim 4, the same disclosure on page 5 of the Specification that related to claim 2 applies to claim 4. Thus claim 4 was amended to recite an additional fixing step.

For all the reasons set forth above, the drawings, the Specification, and all the claims, are now believed to be in complete compliance with the requirements of 35 U.S.C. 112. Withdrawal of this ground of rejection is respectfully requested.

Reconsideration and withdrawal are respectfully requested, for the rejection of claims 19 to 24 under 35 U.S.C. 102 as anticipated by, or in the alternative, under 35 U.S.C. 103 as obvious over *Srinivasan U.S. Patent No. 5, 830,555*.

On Page 2 of this Office Action, it is stated that the process claims 1 to 6, 8, 9 and 11 to 17 are patentable over the prior art of record.

Because claims 19 to 24 were previously directed to the product, but now have been amended to now depend from the method claims depending on claim 1, claims 19 to 24, and new claim 25 are believed to be allowable. Withdrawal of these grounds of rejection under 35 U.S.C. 102 and 35 U.S.C. 103 is respectfully requested.

Applicant would like to draw attention to DE 2 015 243, which was published on October 8, 1970. An English language equivalent of this German publication is GB 1 287 063. Both documents are attached. This patent family discloses to perforate a nonwoven fabric by use of a needle-like device in addition with a current of gas being blown in the opposite direction of the penetrating needle-like device. The perforated nonwoven fabric is impregnated afterwards to stiffen this


material. Therefore, this prior art teaches the perforating of a nonwoven fabric without any suggestion of using a calendar roller arrangement for bonding. Also there is no disclosure that the fibers randomly placed in a perforated belt will form a fibrous web which becomes perforated before being bonded. All of this indicates that this prior art reference does not teach the claimed invention. Enclosed is PTO Form 1449 listing both DE 2,015,243 and GB 1, 287,063.

A check for the U.S.P.T.O. surcharge fee of \$180.00 is enclosed to pay for the filing and the consideration of the prior art reference at this stage of the prosecution. The Commissioner of Patents and Trademarks is hereby authorized to charge any additional required fee, or the credit any overpayment, to Deposit Account No. 03-2468.

In summary claims 1 to 6, 8, 9, 11 to 17 and 19 to 24 are pending and are now believed to be allowable. A prompt notification of allowability is respectfully requested.

Respectfully submitted,

STEFAN ETZOLD ET AL


Allison C. Collard, Reg No. 22,532
Edward R. Freedman, Reg.No. 26,048
Attorneys for Applicants

COLLARD & ROE, P.C.
1077 Northern Boulevard
Roslyn, New York 11576
(516) 365-9802
ERF:dm

- Enclosures: (1) Marked-Up Version of Amended Claims and Drawings
(2) Copy Petition One Month Extension of Time
(3) Substitute Specification and Marked-Up Copy
(4) Copy of DE 2,015,243
(5) Copy of GB 1,287,063
(6) PTO Form 1449 and check for \$180.00

I hereby certify that this correspondence is being deposited with the United States Postal Service as first class mail in an envelope addressed to:
COMMISSIONER FOR PATENTS, P.O.BOX 1450 ALEXANDRIA, VA 22313-1450 on May 1, 2003


Maria Guastella

R:\Patents\E\ETZOLD ET AL -1 PCT\ETZOLD AMDMT IN RESPONSE TO HFOA.wpd



RECEIVED
MAY 09 2003
GROUP 1700

MARKED-UP

VERSION OF

SPECIFICATION

INSERT



PROCEDURE FOR CREATING A FLEECE MADE OF FIBERS

RECEIVED
MAY 09 2003
GROUP 1700

CROSS REFERENCE TO RELATED APPLICATIONS

Applicants claim priority under 35 U.S.C. §119 of German Application No. 198 27 567.6 filed June 20, 1998. Applicants also claim priority under 35 U.S.C. §120 of PCT/DE99/01793 filed June 18, 1999. The international application under PCT article 21(2) was not published in English.

The invention concerns a procedure to make a fleece consisting of fibers with numerous hole structures extending over the entire cross-section, and a fleece manufactured according to this procedure.

One-layer or multilayer fleeces with hole structures extending over the entire cross-section are e.g. used for coverstock materials for articles of hygiene such as sanitary napkins and diapers, or for other textile or technical uses. The hole structures serve to quickly drain bodily fluids, tissue components and feces into the liquid-absorbing material of diapers, sanitary napkins, etc. Depending on the application, the fleeces can be single-layer or multilayer, whereby multilayer fleeces can be bonded with other sheet media such as films.

INSERT



RECEIVED
MAY 09 2003
GROUP 1700

There are several prior-art procedures to introduce hole structures into a one-layer or multilayer fleece, whereby the common element of the prior-art procedures is that the hole structures are created in the finished fleece after bonding and especially thermobonding.

For example, a prior-art procedure in EP 0 687 757 A2 introduces hole structures into the bonded fleece by passing the fleece between heated stamps that are pressed together to melt holes in the bonded fleece. A similar prior-art procedure, a hot-needle punching procedure, is in US 5 709 829.

The advantage of this procedure is that the bond of the fleece structure is held due to the melted edges that arise around the holes. A disadvantage is that the softness is negatively influenced by the relatively hard melted edges. A fleece obtained in this manner feels relatively hard and can be unpleasant to users.

In DE 34 16 004 A1, there is a prior-art process in which an unbonded fleece of thermoplastic fibers is fed to a calender roller arrangement, and the thermoplastic material is melted and displaced by pressure in the area of the holes by the calender roller arrangement. This produces a liquid bump at the edge of the holes to form a bonded grid

PROCEDURE FOR CREATING A FLEECE MADE OF FIBERS

The invention concerns a procedure to make a fleece consisting of fibers with numerous hole structures extending over the entire cross-section, and a fleece manufactured according to this procedure.

One-layer or multilayer fleeces with hole structures extending over the entire cross-section are e.g. used for coverstock materials for articles of hygiene such as sanitary napkins and diapers, or for other textile or technical uses. The hole structures serve to quickly drain bodily fluids, tissue components and feces into the liquid-absorbing material of diapers, sanitary napkins, etc. Depending on the application, the fleeces can be single-layer or multilayer, whereby multilayer fleeces can be bonded with other sheet media such as films.

There are several prior-art procedures to introduce hole structures into a one-layer or multilayer fleece, whereby the common element of the prior-art procedures is that the hole structures are created in the finished fleece after bonding and especially thermobonding.

For example, a prior-art procedure in EP 0 687 757 A2 introduces hole structures into the bonded fleece by passing the fleece between heated stamps that are pressed together to melt holes in the bonded fleece. A similar prior-art procedure, a hot-needle punching procedure, is in US 5 709 829.

The advantage of this procedure is that the bond of the fleece structure is held due to the melted edges that arise around the holes. A disadvantage is that the softness is negatively influenced by the relatively hard melted edges. A fleece obtained in this manner feels relatively hard and can be unpleasant to users.

DELETE THIS PAGE

In another prior-art procedure, the hole structures are created by (cold) stamping/cutting the fibers out of the bonded fleece. Such procedures have the advantage that hard stamped or melted edges do not arise, and materials obtained in this manner are soft. A disadvantage is that this procedure can only be done when the fleece is conveyed at a slow speed. In addition, the fibers are shortened along the holes which decreases the strength of the fleece.

A disadvantage of the cited procedures is that material is unnecessarily destroyed or wasted by hot and cold stamping or burning.

In another prior-art procedure in EP 0 214 608 A2, the fleece is manufactured and the hole structures are created by two rollers between which the fleece is guided. One roller has numerous heated needles, and the other roller has corresponding holes to receive the needles of the first roller. The needles purportedly displace the fibers while forming the hole structures and simultaneously form recesses around the hole structures, and they seal the edges of the hold structures by melting the fibers. In this procedure, the fibers are not shortened or destroyed, however hard melted edges arise that negatively influence the softness. In addition, it is involved and expensive to introduce hole structures after the fleece is thermobonded.

The problem of the invention is therefore to create a procedure that enables professionals to manufacture a fleece with hole structures that feels soft, the bond of the fibers is not weakened by introducing hole structures, the procedure can be done without waste, and it is simple and economical.

This problem is solved with a procedure of the initially-cited type that has the features of patent claim 1.

According to the invention, the fibers are randomly deposited on a screen belt to form a fibrous web in a first step of a procedure to create a fleece made of fibers with numerous hole structures extending over the entire cross-section of the fleece. In a second step, the fibrous web is transported to a hole-structure-creating machine; in a third step, the hole structures are created by mechanically displacing the fibers. The displacement of the fibers does not influence their mechanical and chemical structure. In a fourth step, the fibrous web with the hole structures is bonded in a bonding unit to form a fleece.

The invention is therefore based on the surprising knowledge that, to generate hole structures, it is sufficient to displace the fibers that cover the area of the holes to be formed and compress the fibers in this area and/or the neighboring area without having to destroy or impair the fibrous web in the area of the holes to be formed and/or its general appearance. In brief, the fibers of the fibrous web are reoriented in the area of the hole structures or diverted from their prior course in the procedure according to the invention before manufacturing the fleece by bonding and possibly thermobonding without requiring a heat treatment or simultaneous compression.

Suitable fibers or filaments for creating a fleece by the procedure according to the invention are any fibers or filaments suitable to form fleeces according to the various procedures, especially staple fibers, endless filaments, and bicomponent fibers and filaments. In particular, staple fibers are highly suitable.

It is particularly advantageous that no unnecessary waste or lost material arises, that the fibers are not shortened or destroyed in the area of the hole structures, and that the softness of the finished fleece is very good, and that

no additional hardening at the edge of the hole structures impairs the softness of the finished fleece.

Such a solution has not been pursued to date since in particular in a prior-art process in EP 0 214 608 A2 it is assumed that the fibers would tend to return to their original position after being displaced due to the return effect which would eliminate the created hole structures. It was surprisingly shown that this return effect is irrelevant in the procedure according to the invention.

Before the third step, the fibrous web can be bonded to one or more fleeces and/or with another sheet medium such as a film.

In addition, the danger of the fibers springing back can be advantageously countered by feeding the fibrous web directly to the bonding unit after creating the hole structure. In such a bonding unit, e.g. a calender roller arrangement, the fibrous web is compressed to create the finished fleece and, in an advantageous embodiment of the invention, it is simultaneously thermobonded. A very short path is desirable so that the hole structure is not lost while the fleece is being transported from the hole-structure-creating unit to the bonding unit.

In another advantageous embodiment of the invention, the fibrous web is prebonded before the third step so that the tensile strength of the prebonded fibrous web is 0.1 to 75 % and especially 50 % of the tensile strength of the bonded fleece.

The unbonded fibrous web is more-or-less held by a few widely-spaced bonding points or by applying pressure and/or heat. This provides a certain amount of mechanical stability to the fibrous web so that it can be transported

faster to the hole-structure-creating unit. The faster speed enables faster manufacturing.

In an advantageous embodiment of the procedure, the fibers surrounding the hole structures are fixed before feeding the fibrous web to the bonding unit. This serves to prevent the hole structures from stretching while transporting the fibrous web with the hole structures. Fixing the fibers, i.e., slightly adhering the fibers around the hole structure can be done with suitable means such as by applying heat and/or pressure to the fibrous web, e.g. by smooth rollers.

In addition, the fourth step can be carried out with the hole-structure-creating unit directly after the third step. In this case, the hole structure-creating unit is simultaneously used for bonding.

In a practical embodiment of the invention, the hole-structure-creating unit has two elements with facing surfaces between which the fibrous web is guided, whereby the surface of a first element has numerous barbs facing the fibrous web, and whereby the surface of a second element has openings in which the barbs of the first surface can at least partially enter, whereby the fibers of the fibrous web below the barbs are displaced without being destroyed when the barbs sink into the openings and the hole structures are formed.

In an advantageous embodiment of the invention, the openings of the second surface communicate with a source for a vacuum or pressure such as a blower so that fibers of the fibrous web in the area of the openings are sucked into or blown out of the openings. By sucking the fibers into the openings of the second surface, such a blower can support the nondestructive displacement of the fibers to form the hole structures, and the blower can blow the

fibrous web with the hole structures away from the second surface to gently prevent potential adhesion of the fibrous web to the second surface after creating the hole structures.

The channels and openings of the vacuum source can be shaped and dimensioned so that the fibers to be deformed or reoriented that are sucked into the openings and channels of the vacuum source are not caught.

In another advantageous embodiment of the invention, the first element is a roller. In practical embodiments of the invention, the roller has a diameter of 100 - 500 mm. Such a roller can be advantageous when a relatively fast production speed is to be attained.

In an alternate embodiment of the invention, the first element is a raising and lowering plate. Such a plate that can create discontinuous hole structures can be advantageous when the fibers are to be slowly and carefully displaced.

In practical embodiments of the invention, the barbs of the first element are conical or have an involuted shape or an ogival cross-section, whereby the barbs can have a practical height of 0.5 - 5 mm. Various shapes, sizes and heights of the barbs are used depending on the requirements of the fleece to be created that can be single-layer or multilayer fleece, e.g. a SMS fleece or a combination of fleece and other sheet media.

In another practical embodiment of the invention, the second element is a perforated belt. The fibrous web to be treated can be placed on such a perforated belt and transported to the first element where the barbs of the first element penetrate through the fibrous web into the holes of the perforated belt. Alternately, the second

element can be calender roller. A calender roller would also be used as the second element.

In another practical embodiment of the invention, a fleece created by the procedure according to the invention has hole structures with a diameter of 0.5 - 5 mm, the bonding surface is 3 - 40 % of the fleece surface, and the number of bonding points is 20 - 120 per square centimeter. Such a number of bonding points and a corresponding diameter of hole structures ensures a sufficient number of bonding points at the edge of the hole structures, and this fixes the hole structure so that the displaced filaments around the hole structures after hardening and thermobonding no longer return to their original position.

Other advantages and embodiments of the invention will be portrayed with reference to exemplary embodiments in the following description, the drawing, and in the patent claims. Shown in the drawing are:

Fig. 1 A schematic portrayal of a system for the procedure according to the invention,

Fig. 2 A detailed view of a hole-structure-creating unit of the system from Fig. 1,

Fig. 3 A top view of a hole structure of a fleece created by the procedure according to the invention, and

Fig. 4 An alternative embodiment of a system for the procedure according to the invention viewed from the side.

Fig. 1 shows a first embodiment of a system 10 for the procedure according to the invention. With a suitable and schematically portrayed device 12, a fibrous web 18 of fibers 14 is created and placed on a screen belt 16. As

indicated with the arrow A, a fibrous web 18 consisting of fibers 14 is transported to a hole-structure-creating unit 20. This hole-structure-creating unit 20 consists of a roller 22 whose outer surface 24 that forms the first surface 24 of the hole-structure creating unit 20 is above a perforated belt 26 with a surface 28 that faces the roller 22. This surface 28 forms the second surface 28 of the hole-structure creating unit 20.

The surface 24 of the roller 22 is provided with numerous barbs 30 that can at least partially enter the holes 32 in the perforated belt 26. As indicated by arrow B, the roller 22 rotates counterclockwise. Corresponding to the speed at which the perforated belt 26 is conveyed, the barbs 30 (of which only three are illustrated in Fig. 1 for the sake of simplification) continually penetrate the holes 32 and displace the filaments 14 of the fibrous web 18 at this site.

Under the perforated belt 26 is a vacuum/pressure source that will be discussed further below. *FIG. 1 shows pressure source 34.*

After the fibrous web 18 has passed through both surfaces 24, 28, the fibrous web 18 that now has hole structures 36 reaches a bonding unit 38. This bonding unit 38 consists of two calender rollers 40, 42 in the arrangement 10 in Fig. 1. The fibrous web 18 undergoes thermal bonding from the calender rollers 40, 42 so that the finished fleece 44 leaves the calender rollers 40, 42.

Fig. 2 shows details of the hole-structure-creating unit 20 on a much larger scale than Fig. 1. As indicated by arrow C, the vacuum ~~pressure~~ ^{34a} source ~~34~~ generates a vacuum which sucks the filaments 14 of the fibrous web 18 over the hole 32 of the perforated belt 26 are sucked into the hole 32. This creates a sort of trough through which the barbs 30 of the roller 32 can more easily penetrate through the fibrous

web 18 into the holes 32 so that the filaments 14 of the fibrous web 18 are not destroyed but rather only displaced or reoriented in the area of the hole 32 to be formed.

To make it easier to remove the fibrous web 18 from the perforated belt 26 after the hole structure 36 is generated, it is possible to create pressure to lift the filaments that hang in a hole 32 of the perforated belt 26 so that the filaments 14 cannot contact the edge 46 of the hole 32 when the fibrous web 18 is lifted from the perforated belt 28.

Fig. 3 shows a detailed example of a hole structure 36 in a fleece 44 created by the procedure according to the invention. As can be seen, the fleece 44 has numerous bonding sites 48 created by the calender rollers 40, 42 that are evenly distributed over the entire surface of the fleece 44. By correspondingly adjusting the size, number and distribution of the bonding points, it is possible to provide the hole structure 36 with a sufficient number of bonding points at the edge 50 as well so that the bonding points 48 stabilize the hole structure 36.

Fig. 4 shows a partial area of a second embodiment of a system 10a for the procedure according to the invention. Here as well, the hole-structure-creating unit 20a has a roller 22 corresponding to the roller 22 in Fig. 1. The second surface 28a is the outer surface of the calender roller 40a. Correspondingly, the surface 28a of the calender roller 40a is provided with holes 32a that can be penetrated by barbs 30 of the roller 22. These holes 32a are also connected to a vacuum source (not shown).

The arrangement 10a shown in Fig. 4 makes it possible to dispense with the perforated belt 26 and shorten the transport path from the hole-structure-creating unit 20a to

the bonding unit 38a in contrast to the arrangement 10 in Fig. 1.

MARKED-UP VERSION
OF AMENDED
CLAIMS AND DRAWINGS

1. (Twice Amended) A procedure to create a fleece (44) made of fibers (14) with numerous hole structures (36) extending over the entire cross-section of the fleece (44), comprising:

- in a first step, the fibers (14) are randomly placed on a perforated belt (16) to form a fibrous web (18),
- in a second step, the fibrous web (18) is transported to a hole-structure-creating unit (20; 20a),

-in a third step, [-] the hole-structure-creating unit (20; 20a) is a calendar having two rollers [(22,26; 40A)] with facing surfaces (24, 28; 28a) between which the fibrous web (18) is guided, [whereby] and the surface (24) of a first roller has numerous barbs (30) facing the fibrous web (18) and [whereby] the surface (28; 28a) of a second roller (26; 40a) has openings (32, 32a) in which the barbs (3) of the first surface (24) can at least partially enter, [whereby] such that the fibers (14) of the fibrous web (18) below the barbs (30) are displaced without being destroyed when the barbs (30) sink into the openings (32; 32a) and the hole structures (36) are formed without a heat treatment or simultaneous compression, and

[- in a third step], the hole structures (36) are created by mechanically displacing the fibers (14), [whereby] and the displacement of the fibers (14) does not influence their mechanical and chemical structure, and

-in a fourth step, directly after creating the hole structure, the fibrous web (18) with the hole structures (36), is bonded in a calendar roller arrangement (38; 38z) to form a fleece (44).

2. (Twice Amended) A procedure according to claim 1, wherein the fibrous web is additionally transformed by stiffening and thermobonding to form a fleece (44).

3. (Twice Amended) A procedure according to claim 2, wherein before the third step, the fibrous web (18) is prebonded so that the tensile strength of the prebonded fibrous web (18) is 0.1 to 75% [and especially 50%] of the tensile strength of the bonded fleece (4).

4. (Three Times Amended) A procedure according to claim 1, wherein the fibers (14) surrounding the hole structures (36) are additionally fixed before feeding the fibrous web (18) to the bonding unit (38; 38a).

5. (Three Times Amended) A procedure to create a fleece (44) made of fibers (14) with numerous hole structures (36) extending over the entire cross-section of the fleece (44), comprising:

- in a first step, the fibers (14) are randomly placed on a perforated belt (16) to form a fibrous web (18),
- in a second step, the fibrous web (18) is transported to a hole-structure-creating unit (20; 20a),
- in a third step, the hole-structure-creating unit (20; 20a) is a calendar having two rollers with facing surfaces (24, 28; 28a) between which the fibrous web (18) is guided, and the surface (24) of a first roller has numerous barbs (30) facing the fibrous web (18) and the surface (28; 28a) of a second roller (26; 40a) has openings (32, 32a) in which the barbs (3) of the first surface (24) can at least partially enter, such that the fibers (14) of the fibrous web (18) below the barbs (30) are displaced without being destroyed when the barbs (30) sink into the openings (32; 32a) and the hole structures (36) are formed without a heat treatment or simultaneous compression, and

the hole structures (36) are created by mechanically displacing the fibers (14), and the displacement of the fibers (14) does not influence their mechanical and chemical structure, and

-in a fourth step, directly after creating the hole structure, the fibrous web (18) with the hole structures (36), is bonded in a calendar roller arrangement (38; 38a) to form a fleece (44); and

[A procedure according to claim 1,]

wherein the fibrous web (18) is fed directly to the bonding unit (38; 38a) after the hole structure (36) is created.

8. (Twice Amended) A procedure according to claim 1, wherein the openings (32; 32a) of the second surface (28; 28a) communicate with a vacuum source [(34)] so that fibers (14) of the fibrous web (18) in the area of the openings (32; 32a) are sucked into the openings (32; 32a).

9. (Twice Amended) A procedure according to claim 1, wherein the openings (32; 32a) of the second surface (28; 28a) communicate with a pressure source [(34)] so that fibers (14) of the fibrous web (18) in the area of the openings (32; 32a) are blown out of the openings (32; 32a).

11. (Twice Amended) A procedure according to claim 1, wherein the roller [(22)] has a diameter of 100-500 mm.

12. (Three Times Amended) A procedure according to claim 1, wherein the first element [(22)] is a lowering and raising plate.

13. (Three Times Amended) A procedure according to claim 1, wherein the barbs (30) of the first element [(22)] are conical.

17. (Three Times Amended) A procedure according to claim 1, wherein a [the] second element [(26)] is a perforated belt [(26)].

19. (Three Times Amended) A [fleece (44) created] procedure according to [a] [procedure in] claim 1, wherein the hole structures (36) have a diameter of 0.5-5 mm.

20. (Twice Amended) A [fleece] procedure according to claim 19, wherein the bonding surface is 3-40% of the fleece surface.

21. (Three Times Amended) A [fleece] procedure according to claim 19, wherein the number of bonding points (48) is 20 -120 per square.

22. (Three Times Amended) A [fleece] procedure according to claim 19, wherein the shape of the hole structures (36) is noncircular.

23. (Three Times Amended) A [fleece] procedure according to claim 19, wherein the distance between individual hole

structures (36) is irregular.

24. (Three Times Amended) A [fleece (44) manufactured] procedure according to claim 1, wherein the fibrous web (18) is bonded to at least one other sheet medium before creating the hole structures (36).

R:\Patents\E\ETZOLD ET AL -1 PCT\ETZOLD AMDMT IN RESPONSE TO NFOA.wpd